

Non-Asbestos Fibre Gasket Material



CNAF C4324 DATA SHEET

DELTA RUBBER LIMITED

Unit 21 Priory Industrial Park, Airspeed Road
Christchurch, Dorset, BH23 4HD

t: 01425 278011 www.deltarubber.co.uk deltasales@deltarubber.co.uk

Description

An economic grade based on mixture of aramid and glass fibres with a nitrile rubber binder. Suitable for general industrial service including oils, hydrocarbons, low pressure steam and water.

Technical Information

Compressibility ASTM F 36 A	10%
Recovery ASTM F 36 A	55%
Stress Relaxation DIN 52913	20Mpa
Stress Relaxation BS 7531	23Mpa
Klinger cold/hot compression (50Mpa) – Thickness decrease 23°C	11%
Decrease at 300°C	26%
Gas leakage according to DIN 3536/6	<0.1ml/min
Chlorides (soluble)	150ppm
Thicknesses increases after fluid Immersion ASTM F 146	0-10%
Density	1.85g/cm ³

Thickness

0.4mm – 3.0mm

Sheet Size

1.5m x 2m

Finish

Plate Finish

